



GlassInspector

Daily report

Date: 2022/07/21


- Scanner results per defect type:
 - Total glass count: **2134**
 - Without defects: **1134 (53%)**
 - With defects: **1000 (46.9%)**
 - Thick scratch: **83 (8.3%)**
 - Scratch in coat: **300 (30%)**
 - Defect in coat: **200 (20%)**
 - Opaque stain: **67 (6.7%)**
 - Transparent stain: **170 (17%)**
 - Inclusion: **180 (18%)**



GlassInspector


- Operator reports per defect:

○ Total glass count:	2134
○ Without defects:	1471 (68.9%)
○ With defects:	663 (31.1%)
■ Thick scratch:	75 (11.3%)
■ Scratch in coat:	266 (40%)
■ Defect in coat:	172 (25.9%)
■ Opaque stain:	0 (0%)
■ Transparent stain:	0 (0%)
■ Inclusion:	150 (22.9%)



GlassInspector

- Evaluation of operator actions:
 - Total glass count: **2134**
 - Without defects (scanner): **1134 (53%)**
 - With defects (scanner): **1000 (46.9%)**
 - Accepted by operator: **1471 (68.9%)**
 - Rejected by operator: **663 (31.1%)**



GlassInspector

- Reasons and duration for production interruption in minutes:

- Total time interrupted: **72**
- Washer down: **17 (23.6%)**
- Spacer missing: **32 (44.4%)**
- Others: **23 (31.9%)**

